

Kent Balusters



Tools and Materials

String Line

3 Ft Level (including horizontal and vertical sight)

20mm Dia Masonry drill bit (marked with tape @ 50mm)

Angle grinder and stone cutting disc (if cutting stones to fit an exact length)

Bricklayers trowel and pointing trowel

Soft sand (building sand)

Ordinary Portland cement

Pointing mixture- 4:1 mix of silica sand : white cement
(available from Kent Balusters)

As every component of the Hever balustrade sits on top of the plinth course, it is important to lay this course with care because it will dictate the position of every other piece of the balustrade. First, lay out the plinth course (and any corners) roughly to ensure that you have enough stonework, check that the area is level enough to build the balustrade on and calculate any cuts that will need to be made.

Mix a mortar bed of 5 parts soft sand to 1 part OP cement to go under the plinth course. Lay the plinth course on the mortar bed using a string line and level to keep it straight and level. Ensure that some mortar finds its way into the hollow channel underneath the plinth to key the sections together.

When mortar squeezes out of a joint between stones, leave it until it stiffens (1-3 Hrs) and then rake some of it out of the joint. This leaves a recess for the pointing mixture at a later time. By raking it back once it has dried slightly you will not smear the edges of the stone with grey mortar, if any mortar does get onto the surface of the stonework then just leave it to set and clean it once all of the construction is finished.

Next place the die blocks and corner dies in position on a 5-10mm bed of 3:1 mortar. (For extra security the die blocks may be drilled and pinned to the plinths). Ensure the dies are in the correct position using a vertical level. Now measure the distance between two dies, calculate and mark the positions of the holes for the baluster retaining pins.

The holes for the baluster retaining pins can now be drilled into the plinth (20mm dia and 50mm deep). Clean the holes and then fix the balusters in position on beds of 3:1 mortar (the beds should be the same thickness as the beds under the die blocks). Use a string line and vertical level to fix the balusters and ensure that the spacings between them are equal. Again allow this mortar to stiffen and then rake back the joints. The mortar holding the balusters should now be allowed to set (24 Hrs if poss).

Mark and drill 20mm dia X 50mm holes in the copings to accept the top retaining pins of the balusters and then fix the copings onto the tops of the balusters and dies using 3:1 mortar. Start work from one end of the balustrade and use the string line and level to keep the copings straight and level. Frogs have been cast into the ends of the copings, when filled with mortar they will form a secure key between the copings. Rake back the excess mortar from the joints as before.

The balustrade is now ready for pointing. Only mix up a small amount of pointing mixture at any time (about a coffee mug). Add water until the mixture has the same consistency as toothpaste. Excess water will cause the mixture to smear and stain either side of the joint. Point up using the tip of a pointing trowel or small pointing tool. Once the mortar and pointing mixture has set and hardened, any mortar spills or stains can be removed by the following method:

Cleaning

Cleaning is best done with a 16% Hydrochloric Acid solution, this is sold in DIY and Hardware shops as 'Patio Cleaner'. Observe the safety precautions on the container.

Soak the stained area with a hose pipe for several minutes so that the water is no longer being absorbed by the stonework. Apply patio cleaner to the stained area with a paint brush and it will fizz for a few seconds, hose the solution off and apply again. Repeat this until the stain has disappeared.

Additional Suggestions

- When cutting your balustrade to fit an exact length (ie. sitting on a wall), cut a small amount off several pieces. You will not use any more stones and you will get a better looking job than having just one section cut short.

- Although diamond cutters will produce a cleaner edge, cutting can be done with an ordinary stone cutting disc on an angle grinder. Mark and cut all the way around the stone before cutting right through it.

- After drilling or cutting stones, brush off any loose dust and hose the area clean - this will avoid colour variations which can be produced if the dust remains on the stone.

- To speed up the process of construction, a two part chemical fixing resin can be used instead of soft sand and cement mortar. If this is being used then the stonework should be completely dry before you start and great care should be taken to avoid smears and spots on the stones as the cleaning process above will not remove chemical fixings.